



EASY FUSE


An 82 C.O.E. fusible by Youghioghney

Easy Fuse - 82 C.O.E.


These glass styles are thoroughly tested using a dilatometer to measure the actual coefficient of thermal expansion and fusing tests with readings using a polariscope. This is to assure that the product is as close as possible to a set standard. Because Youghioghney has no control over the manufacture of float glass, we make no warranties, whether expressed or implied, to the fitness for a particular purpose. We urge you to test this product on the commercially available float glass in your area before undertaking any major fusing project.

The Youghioghney testing laboratory uses PPG Carlisle, Pa. 3mm and 5mm float glass with the following firing schedule (remember this is only a guide):

- From room temp. to 800°F at 300° per hour, hold for 10 minutes.
- From 800°F to 1120°F at 300° per hr., hold for 10 minutes.
- From 1120°F to 1250°F at 200° per hr., hold for 10 minutes.
- From 1250°F to 1560°F fairly quickly, hold for 10 minutes.
- Crash from 1560°F to 1090°F, hold for 45 minutes.
- From 1090°F to 970°F at 100° per hr., hold for 45 minutes.
- From 970°F to 830°F at 100° per hr., hold for 30 minutes.
- From 830°F to 720°F at 100° per hr., hold for 1 minute.
- Natural cooling to room temperature
- Please adjust hold times for the size of your project.




EF-200-LG A
EF-200-SM A
Amber




EF-209-LG A
EF-209-SM A
Champagne



EF-300-LG A
EF-300-SM A
Black




EF-303-LG A
EF-303-SM A
Purple




EF-304-LG A
EF-304-SM A
Pale Plum




EF-306-LG A
EF-306-SM A
Violet




EF-403-LG A
EF-403-SM A
Pea Green




EF-404-LG A
EF-404-SM A
Kelly Green




EF-430-LG A
EF-430-SM A
Olive Green



EF-444-LG A
EF-444-SM A
Emerald Green




EF-500-LG** B
EF-500-SM** B
Yellow




EF-504-LG** B
EF-504-SM** B
Chartreuse



EF-506-LG** B
EF-506-SM** B
Apple Green




EF-509-LG** B
EF-509-SM** B
Tangerine



EF-550-LG** B
EF-550-SM** B
Marigold



EF-600-LG A
EF-600-SM A
Cobalt Blue



EF-601-LG A
EF-601-SM A
Light Blue

Sheet size (approx.):

-LG 18" x 24"

-SM 12" x 18"

Sample Box: Order as EF5B

**Indicates "striking color".

EASY FUSE MINI PACK

82 C.O.E. Fusible glass by Youghioghney.

Each pack contains 12 assorted colors cut approx. 9" x 12". **Order as:** EF-MINI




Illustrations represent fired colors. Some styles appear as an entirely different color before firing. Firing schedule may affect the way colors strike.

Note: Some opals may appear Transparent or Translucent before firing.

**Indicates "striking color".

Frits and Powders


8 oz. jars: Coarse, Medium, Fine & Powder
See page A28.




EF-606-LG A
EF-606-SM A
Turquoise




EF-666-LG A
EF-666-SM A
Sea Blue



EF-700-LG A
EF-700-SM A
Gray



EF-705-LG** C
EF-705-SM** C
Cranberry




EF-706-LG** C
EF-706-SM** C
Gold Purple




EF-707-LG C
EF-707-SM C
Erbium Pink




EF-777-LG** C
EF-777-SM** C
Neo



EF-900-LG** B
EF-900-SM** B
Red



EF-901-LG** B
EF-901-SM** B
Red-Orange



EF-905-LG** B
EF-905-SM* B
Orange




EF-1000-LG** D
EF-1000-SM** D
White Opal



EF-2000-LG** D
EF-2000-SM** D
Pina Colada Opal



EF-4200-LG** D
EF-4200-SM** D
Mustard Seed Opal



EF-4060-LG** D
EF-4060-SM** D
Bay Leaf Opal




EF-4061-LG** D
EF-4061-SM** D
Seafoam Opal




EF-4066-LG** D
EF-4066-SM** D
Dark Sea Mist Opal



EF-4444-LG** D
EF-4444-SM** D
Emerald Green Opal



EF-5000-LG** B
EF-5000-SM** B
Lemon Yellow Opal



EF-5500-LG** B
EF-5500-SM** B
Marigold Opal




EF-6400-LG** D
EF-6400-SM** D
Wedgewood Blue Opal




EF-7077-LG** D
Lt. Dolphin Gray
Opal



EF-7777-LG** D
EF-7777-SM** D
Thunder Gray Opal



EF-9000-LG** B
EF-9000-SM** B
Red Opal



EF-9500-LG** B
EF-9500-SM** B
Orange Opal



EF-9052-LG** B
EF-9052-SM** B
Blush Pink Opal